Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP-2018-02-07-09 **Date: 10-02-18**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at Munnikondappa Layout in Bagalagunte ward No.14
Agency	:	Sri.Sree RamaReddy, #62, Behind Widia, Ashok Nagara, Nagasandra (P), Bangalore.
Customer's Reference	:	EE/DD/LOA/1658/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-02-18
Sample ID No	:	2018-02-07-09 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2,3,4,5, 6,11) 1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	08-02-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.29	–
2	Finess by Air permeability method (m^2/kg.Min)	298.6	225m^2/kg. Min
3	Density (gm/cc)	3.13	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time	155 minutes	Not less than 30 minutes
6	Final Setting time	265 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.0mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative.

Any correction in the report will make this report invalid.

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate.

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP-2018-02-07-09 **Date: 08-03-18**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at Munnikondappa Layout in Bagalagunte ward No.14
Agency	:	Sri.Sree RamaReddy, #62, Behind Widia, Ashok Nagara, Nagasandra (P), Bangalore.
Customer's Reference	:	EE/DD/LOA/1658/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-02-18
Sample ID No	:	2018-02-07-09 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	08-02-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	56.5N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO BANGALORE Sig. Date

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444601 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

TEST REPORT OF AGGEGRATE IMPACT VALUE

IS: 2386 Part IV

Lab ID	:	**CP-RW-2018-02-06-11** **Date: 07-02-18**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at Munnikondappa Layout in Bagaalagunte ward No.14
Agency	:	Sri.Sree RamaReddy, #62, Behind Widia, Ashok Nagara, Nagasandra (P), Bangalore.
Customer Reference	:	EE/DD/LOA/1658/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-02-18
Sample ID No	:	2018-02-06-11/01
Type of Mix	:	Course Aggregate for WMM (Wet Mix Macadam)
Date of test	:	06-02-18

Sl.No	Particulars of observations	Index	TEST 1	TEST 2
1	Total weight of the surface dry sample sample (passing 12.5 mm and retained on 10mm sieve)	A	309.0	309.0
2	Weight of fraction passing 2.36mm sieve After giving 15 blows	B	68.0	76.0
3	weight of fraction retained 2.36mm sieve After giving 15 blows	C	240.7	232.5
4	Total weight of (B+C) is less than the initial weight (Weight A) by more than one gram the result shall be discarded and a fresh test made.	A-(B+C)	0.3	0.5
5	Aggregate impact value	(B/A)*100	22.0	24.6
6	Aggregate impact value (Mean of two tests)	Pecentage	23.3	

Note:-

The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

End of Report

M : 9972924526 | Tel : +91-80-23444801 | e-mail : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

DETERMINATION OF FLAKINESS INDEX AND ELONGATION INDEX OF COARSE AGGREGATE(IS 2386 (Part 1) 1963 (RA 2007)

Lab ID	:	**CP-RW-2018-02-06-11** **Date: 07-02-18**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at Munnikondappa Layout in Bagalagunte ward No.14
Agency	:	Sri.Sree RamaReddy, #62, Behind Widia, Ashok Nagara, Nagasandra (P), Bangalore.
Customer Reference	:	EE/DD/LOA/1658/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-02-18
Sample ID No	:	2018-02-06-11/01
Type of Mix	:	Coarse Aggregate for WMM (Wet Mix Macadam)
Date of test	:	06-02-18

Result:

Index	Percentage of Flakiness and Elongation Index(%)	Secified limits as per MORTH specification table 400-12
Flakiness Index	14.2	Combined Flakiness & Elongation Index for WMM is Maximum 35%
Elongation Index	10.3	
Combined Flakiness and Elongation Index for WMM	24.6	

Note:-
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST RESULTS OF GRADATION FOR WMM

Lab ID	:	**CP-RW-2018-02-06-11** **Date: 07-02-18**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at Munnikondappa Layout in Bagalagunte ward No.14
Agency	:	Sri.Sree RamaReddy, #62, Behind Widia, Ashok Nagara, Nagasandra (P), Bangalore.
Customer Reference	:	EE/DD/LOA/1658/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-02-18
Sample ID No	:	2018-02-06-11/01
Type of Mix	:	WMM (Wet Mix Macadam)
Date of test	:	06-02-18
Oven Dry Weight	:	10000 Grams

IS Sieve Size(mm)	Weight Retained (gm)	Cumulative Weight Retained (gm)	% Cumulative Weight Retained	% Passing	Spec.I.Vide Table 400.13 MORTH Specification
53	0	0	0.0	100.0	100
45	232	232	2.3	97.7	95-100
22.4	2133	2365	23.7	76.4	60-80
11.2	2365	4730	47.3	52.7	40-60
4.75	1321	6051	60.5	39.5	25-40
2.36	1886	7937	79.4	20.6	15-30
0.6	255	8192	81.9	18.1	8-22
0.075	1399	9591	95.9	4.1	0-5

Note:-

The results pertain to the samples received and tested.
All information furnished by Customer/Representative.
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate.

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig. Date

Page 1/1
End of Report